

Title	Understanding the p-toluenesulfonamide/triphenylphosphine oxide crystal chemistry: a new 1:1 cocrystal and ternary phase diagram
Author(s)	Croker, Denise M.; Foreman, Michael E.; Hogan, Bridget N.; Maguire, Nuala M.; Elcoate, Curtis J.; Hodnett, Benjamin K.; Maguire, Anita R.; Rasmuson, Ake C.; Lawrence, Simon E.
Publication date	2012
Original citation	Croker, Denise M., Foreman, Michael E., Hogan, Bridget N., Maguire, Nuala M., Elcoate, Curtis J., Hodnett, Benjamin K., Maguire, Anita R., Rasmuson, Ake C., Lawrence, Simon E. (2012) 'Understanding the p-Toluenesulfonamide/Triphenylphosphine Oxide Crystal Chemistry: A New 1:1 Cocrystal and Ternary Phase Diagram'. Crystal Growth & Design, 12 (2):869-875. http://pubs.acs.org/doi/abs/10.1021/cg201300e
Type of publication	Article (peer-reviewed)
Link to publisher's version	http://pubs.acs.org/doi/abs/10.1021/cg201300e http://dx.doi.org/10.1021/cg201300e Access to the full text of the published version may require a subscription.
Rights	© 2011, American Chemical Society. This document is the Accepted Manuscript version of a Published Work that appeared in final form in Crystal Growth & Design, copyright © American Chemical Society after peer review and technical editing by the publisher. To access the final edited and published work see http://pubs.acs.org/doi/abs/10.1021/cg201300e
Item downloaded from	http://hdl.handle.net/10468/949

Downloaded on 2017-02-12T09:21:49Z

Understanding the *p*-toluenesulfonamide / triphenylphosphine oxide crystal chemistry: a new 1:1 cocrystal and ternary phase diagram

Denise M. Croker,^{†§} Michael E. Foreman,^{†‡} Bridget N. Hogan,^{†§} Nuala M. Maguire,^{†‡} Curtis J. Elcoate,^{†‡} B. Kieran Hodnett,^{†§} Anita R. Maguire,^{†||} Åke C. Rasmuson,^{†§} and Simon E. Lawrence.^{†‡}*

[†] Solid State Pharmaceutical Cluster. [‡] Department of Chemistry, Analytical and Biological Chemistry Research Facility, University College Cork, Cork, Ireland. [§] Materials and Surface Science Institute and the Department of Chemical and Environmental Sciences, University of Limerick, Limerick, Ireland. ^{||}

Department of Chemistry and School of Pharmacy, Analytical and Biological Chemistry Research Facility, University College Cork, Cork, Ireland.

Abstract A novel 1:1 cocrystal between *p*-toluenesulfonamide and triphenylphosphine oxide has been prepared and structurally characterized. This 1:1 cocrystal was observed to form during solid state grinding experiments, with subsequent formation of a known 3:2 cocrystal in the presence of excess sulfonamide. Both cocrystals are stable in the solid state. The ternary phase diagram for the two coformers was constructed in two different solvents: acetonitrile and dichloromethane. Examination of these diagrams clarified solution crystallization of both the newly discovered 1:1 cocrystal and the previously reported 3:2 cocrystal, and identified regions of stability for each cocrystal in each solvent. The choice of solvent was found to have a significant effect on the position of the solid state regions within a cocrystal system.

*Corresponding author: Denise.Croker@ul.ie

Address: Department of Chemical and Environmental Sciences, University of Limerick, Limerick, Ireland

Email: Denise.Croker@ul.ie, Tel.: +353 61 234617, Fax: +353 61 213529.

Understanding the *p*-toluenesulfonamide / triphenylphosphine oxide crystal chemistry: a new 1:1 cocrystal and ternary phase diagram

Denise M. Croker,^{†§} Michael E. Foreman,^{†‡} Bridget N. Hogan,^{†§} Nuala M. Maguire,^{†‡} Curtis J. Elcoate,^{†‡} B. Kieran Hodnett,^{†§} Anita R. Maguire,^{†||} Åke C. Rasmuson,^{†§} and Simon E. Lawrence.^{†‡}*

[†] Solid State Pharmaceutical Cluster.

[‡] Department of Chemistry, Analytical and Biological Chemistry Research Facility, University College Cork, Cork, Ireland.

[§] Materials and Surface Science Institute and the Department of Chemical and Environmental Sciences, University of Limerick, Limerick, Ireland.

^{||} Department of Chemistry and School of Pharmacy, Analytical and Biological Chemistry Research Facility, University College Cork, Cork, Ireland.

E-mail: Denise.Croker@ul.ie

RECEIVED DATE (to be automatically inserted after your manuscript is accepted if required according to the journal that you are submitting your paper to)

TITLE RUNNING HEAD: *p*-Toluenesulfonamide / triphenylphosphine oxide crystal chemistry

ABSTRACT: A novel 1:1 cocrystal between p-toluenesulfonamide and triphenylphosphine oxide has been prepared and structurally characterized. This 1:1 cocrystal was observed to form during solid state grinding experiments, with subsequent formation of a known 3:2 cocrystal in the presence of excess sulfonamide. Both cocrystals are stable in the solid state. The ternary phase diagram for the two coformers was constructed in two different solvents: acetonitrile and dichloromethane. Examination of these diagrams clarified solution crystallization of both the newly discovered 1:1 cocrystal and the previously reported 3:2 cocrystal, and identified regions of stability for each cocrystal in each solvent. The choice of solvent was found to have a significant effect on the position of the solid state regions within a cocrystal system.

Introduction

Cocrystals, crystalline structures composed of two or more neutral components, have the potential to alter the physical properties of solid state materials, and as such are of great interest to the pharmaceutical industry.¹ Research in cocrystallization has greatly increased in recent years; yet large scale production of a commercial cocrystal product remains elusive. This is mainly due to a lack of robustness in cocrystal preparation methods. Solid state grinding, solvent drop grinding and solution methods are routinely used to produce cocrystals,²⁻³ but with a certain element of trial and error involved. The majority of the work to date has focused on discovery of new cocrystal structures, although there has been recent work on understanding the mechanism of formation of cocrystals,⁴⁻¹⁰ as well as combining prediction and experiment to design novel cocrystal forms.¹¹

Ternary phase diagrams can be used to describe the stability of a desired cocrystal in terms of the concentration of both of the coformers in a given solvent.⁴⁻¹⁰ Chiarella *et al.* used ternary phase diagrams to understand the formation of a 1:1 cocrystal of *trans*-cinnamic acid and nicotinamide.⁴ Evaporation of a solution containing stoichiometric amounts of both coformers in methanol yielded the cocrystal, but in water gave only the acid. A phase diagram was constructed by allowing the coformers and the cocrystal to equilibrate individually in methanol and water, with varying coformer ratios. In methanol, it was observed that the solubility curve of the cocrystal crossed the 1:1 stoichiometric ratio line, meaning that it is possible to crystallize the cocrystal from a stoichiometric solution in methanol. In

water the cocrystal solubility curve does not cross the 1:1 stoichiometric ratio line, and thus it is not possible to obtain the cocrystal from a stoichiometric aqueous solution. Rodríguez-Hornedo *et al.* made use of a ternary phase diagram to describe the stability of two cocrystals (2:1 and 1:1 ratios) of carbamazepine with 4-aminobenzoic acid.⁷ Both cocrystals could be obtained from slow evaporation of solutions of the coformers in ethanol, with the cocrystal stoichiometry dictated by the acid concentration. Billot *et al.* used discontinuous isoperibolic thermal analysis (DITA) to produce phase diagrams of an API and glutaric acid in a range of different solvents, and used the results to build a predictive model for cocrystal stability in alternative solvents.⁵ A number of authors have reviewed the thermodynamics involved in cocrystal formation.^{9,12-14}

Triphenylphosphine oxide (Ph₃PO) is an excellent hydrogen-bond acceptor and has therefore attracted attention as a cocrystal coformer.¹⁵ Sulfonamides have also been used as coformers due to their hydrogen-bond donor ability, for example as recently shown by Nangia *et al.*¹⁶ The commonly observed motif is the R₄²(8) ring, usually with a 1:1 stoichiometry. Glidewell *et al.* reported a 3:2 cocrystal of *p*-toluenesulfonamide (TSA) with Ph₃PO,¹⁷ as well as a 1:1 cocrystal of TSA with the related *m*-tritolyphosphine oxide.¹⁸




Figure 1: Chemical structure of (a) *p*-toluenesulfonamide (M.P.=134-137 °C), and (b) triphenylphosphine oxide (M.P. = 154-158 °C).

The cocrystallization of TSA with Ph_3PO was investigated, and herein we report a new 1:1 cocrystal of TSA with Ph_3PO . The formation of the two cocrystals was investigated in the solid state and in solution, and ternary phase diagrams were constructed to identify regions of stability for each cocrystal in two solvents, acetonitrile and dichloromethane.

Experimental Section

Chemicals. *p*-Toluenesulfonamide and triphenylphosphine oxide were obtained from Sigma and used as received. Acetonitrile and dichloromethane were reagent grade.

Solid State Grinding Experiments

Grinding experiments were performed using a Retsch MM400 ball mill fitted with 5 mL grinding jars containing one 2.5 mm stainless steel grinding ball per jar. The mill was operated at 30 Hz frequency. The initial experiment involved grinding a 1:1 ratio of the two coformers for 30 min on a 1 mmol scale. Subsequent experiments were undertaken on a 1 mmol as detailed in Tables 1 and 2.

Crystallization Experiments

p-Toluenesulfonamide (0.171 g, 1.00 mmol) and triphenylphosphine oxide (0.278 g, 1.00 mmol) were dissolved in MeCN (6 mL) and placed in a sample vial. Toluene (4 mL) was layered on top of the solution, and the system left to stand for 21 d to give crystals suitable for single crystal diffraction.

p-Toluenesulfonamide (0.171 g, 1.00 mmol) and triphenylphosphine oxide (0.278 g, 1.00 mmol) were dissolved in CH_2Cl_2 (10 mL), placed in a sample vial and left to stand for 14 d to give crystals suitable for single crystal diffraction.

Large amounts of each cocrystal form were produced by cooling crystallization in a HEL PolyblockTM – a glass reaction vessel with automated heating and cooling provided by a Julabo UC012T-H Unichiller. For the 3:2 cocrystal, *p*-toluenesulfonamide (2.57 g, 0.015 mmol) and triphenylphosphine oxide (4.17 g, 0.015 mmol) were dissolved in CH_2Cl_2 (50 mL), heated to reflux and maintained under reflux for 1 h. For the 1:1 cocrystal, *p*-toluenesulfonamide (5.60 g, 0.033 mmol) and triphenylphosphine oxide (11.23 g, 0.040 mmol) were dissolved in MeCN (50 mL), heated to 70 °C and maintained at this

temperature for 1 h. The solutions were cooled at $0.1\text{ }^{\circ}\text{C min}^{-1}$ to $5\text{ }^{\circ}\text{C}$, and aged for 24 h. The crystals were isolated, washed with the pure crystallization solvent ($\sim 10\text{ mL}$) and dried in a vacuum oven at $50\text{ }^{\circ}\text{C}$ overnight. Cocrystal form was verified using PXRD.

Solubility Measurements

The solubility of pure TSA and Ph_3PO respectively in MeCN and CH_2Cl_2 was determined gravimetrically. Excess solid was charged to solvent at $20\text{ }^{\circ}\text{C}$ and equilibrated with constant agitation for 24 hours, at which point agitation was stopped and the solids allowed to settle for 1 hour. Three 1 ml samples of the clear solution were filtered into preweighed glass vials (M_1), and weighed (M_2). The solvent was allowed to evaporate in a fume hood (24 hours) before transferring the glass vial to a vacuum oven at $50\text{ }^{\circ}\text{C}$ (overnight). The vial was allowed to return to room temperature before weighing the final dry weight (M_3). The formula $(M_3 - M_1)/(M_2 - M_3)$ revealed the solubility, expressed as g solid/g solvent.

The solubility of pure TSA and the 1:1 cocrystal as a function of Ph_3PO concentration in MeCN and CH_2Cl_2 was determined at $20\text{ }^{\circ}\text{C}$ by equilibrating the desired phase in solutions of known Ph_3PO concentration. The solubility of pure Ph_3PO and the 3:2 cocrystal as a function of TSA concentration in MeCN and CH_2Cl_2 at $20\text{ }^{\circ}\text{C}$ by equilibrating the desired phase in solutions of known TSA concentration. Gravimetric analysis as described above was used to calculate solubility, with mass balance used to account for the mass of the known component.

The solubility of the 1:1 cocrystal in MeCN at $20\text{ }^{\circ}\text{C}$ was measured in the same way, but efforts to measure the solubility of the 3:2 cocrystal in MeCN, or the 1:1 or 3:2 cocrystal in CH_2Cl_2 , were unsuccessful due to transformation of the solid form within the equilibration time.

Invariant points, also referred to as eutectic points or transition concentrations, are fixed solution concentrations at which 2 solid phases can exist together in equilibrium; in the present work namely TSA and the 3:2 cocrystal (C_1), the 3:2 cocrystal and the 1:1 cocrystal (C_2), and the 1:1 cocrystal and Ph_3PO (C_3). These points were determined by generating a slurry of the 2 required solid forms, described as (C_1), (C_2), (C_3) above, using the method described by Rodríguez-Hornedo *et al.*¹⁴ The

slurries were equilibrated for 24 h at 20 °C, after which the solvent content of the liquid phase was determined using gravimetric analysis, and the concentration of TSA and Ph₃PO in the liquid phase was determined using HPLC.

The experimental setup for all solubility measurements consisted of a thermostatic water bath (Grant GR150 with S38 stainless steel water bath; 26 L; stability ± 0.005 °C and uniformity ± 0.02 °C @ 37 °C) with a serial magnetic stirrer plate placed on the base. Agitation was provided by use of 10 mm magnetic stirrer bars in 5 ml glass vials.

Construction of the Ternary Phase Diagram

The solubility of the pure substances and the invariant points were converted to mass fraction on a total mass basis (TSA + Ph₃PO + Solvent), and plotted on a ternary axis in both MeCN and CH₂Cl₂ to generate the appropriate ternary phase diagrams using ProSim Ternary Diagram software. Mass fraction was chosen in preference to mole fraction as the use of mole fraction tended to compress the solution phase region making visualization of the solubility curves difficult.

Differential Scanning Calorimetry

DSC was performed on a TA instruments Q1000 incorporating a refrigerated cooling system. Samples (3–5 mg) were crimped in non-hermetic aluminum pans and scanned from 30 to 300 °C at a heating rate of 10 °C/min under a continuously purged dry nitrogen atmosphere.

Single Crystal Diffraction

X-ray diffraction data were collected on a Bruker APEX II DUO diffractometer using graphite monochromatized Mo $K\alpha$ radiation ($\lambda = 0.7107$ Å), and cooled using an Oxford Cryosystems COBRA fitted with a N₂ generator. All calculations were performed using the *APEX2* software suite,^{19,20} and the diagrams prepared using Mercury 2.4.²¹

Powder Diffraction

Powder diffraction data were collected on either a Philips X'Pert-MPD PRO diffractometer with nickel filtered copper Cu $K\alpha$ radiation ($\lambda = 1.5418$ Å), run at 40 kV and 35 mA, $2\theta = 5 - 35^\circ$, with a step size of $0.02^\circ 2\theta$ and a scan speed of $0.02^\circ \text{ s}^{-1}$, or on a Stöe Stadi MP diffractometer with Cu $K\alpha_1$

radiation ($\lambda = 1.5406 \text{ \AA}$) run at 40 kV and 40 mA, $2\theta = 3.5 - 60^\circ$, with a step size of $0.5^\circ 2\theta$ and a step time of 30s.

HPLC Analysis

This was performed on either a Waters Alliance 2690 Separations Module with a Waters 486 Detector using a YMC-Pack ODS-A column (250 mm x 4.6 mm, 5 μm) eluting with MeCN:H₂O (60:40) at 1 mL/min, UV detection at 254 nm, or on a HPLC System consisting of a Shimadzu LC10AT Pump set at 1.5mL/min, Shimadzu SPD-6AV Spectrophotometric detector at 254 nm, a Waters 717 autosampler with a Beckman Coulter Ultrasphere ODS Column (250 mm x 4.5 mm, 5 μm), eluting with MeCN:H₂O (60:40).

Results and Discussion

Solid state grinding

Solid state grinding of an equimolar mixture of TSA and Ph_3PO for 30 min yielded a product which showed the presence of two sharp endothermic peaks at 135 and 139 °C in the DSC analysis, Figure 2. The 3:2 cocrystal is known to have a melting point of 138 °C.¹⁷ The PXRD pattern of this product showed the presence of the known 3:2 cocrystal and extra peaks which were not due to an excess of either starting material.




Figure 2: DSC trace of the product obtained from 30 minute grinding of a 1:1 molar mixture of TSA and Ph_3PO .

Single crystal analysis of crystals obtained from MeCN, melting point 134–136 °C, revealed a novel 1:1 cocrystal (Figure 3). Each amide hydrogen atom is involved in a discrete hydrogen-bond to a phosphine oxygen atom, leading to a discrete four molecule hydrogen-bonded complex containing a R_4^2 (8) ring at the binary level.²² The PXRD data for the unknown material observed in the grinding experiments is consistent with the single crystal data for this new 1:1 cocrystal. Crystals grown from CH_2Cl_2 , melting point 138–140 °C, were found to match the reported 3:2 structure.¹⁷ The X-ray diffraction pattern of each form was generated in Mercury 2.4 from the respective crystallographic information files (CIF) file, and is presented in Figure 4.




Figure 3: The cocrystals of TSA with PPh_3O : (i) the 1:1 cocrystal, left, showing the $\text{R}_4^2(8)$ ring and (ii) the 3:2 cocrystal,¹⁷ right, which also has the $\text{R}_4^2(8)$ motif.




Figure 4: PXRD patterns recorded for the 1:1 (A) and 3:2 (B) cocrystals of TSA and Ph_3PO .

Experimental patterns are shown as solid lines with the corresponding theoretical pattern given as a dotted line.

In order to gain some insight into the stability of the cocrystals, we undertook further grinding experiments. Thus, a 1:1 molar ratio of the two coformers was ground for either a short time (5 min) or a long time (198 min). This was repeated using a 3:2 molar ratio of the coformers. The results (Table 1) suggest that the 1:1 cocrystal is formed first, before transforming into the 3:2 cocrystal if sufficient sulfonamide is present.

Table 1. Effect of reagent composition and grinding time upon cocrystal output

<i>Material input</i>	<i>Grind time (min)</i>	<i>Material output</i>
1:1 ratio of coformers	5	1:1 cocrystal, plus both coformers
1:1 ratio of coformers	198	1:1 cocrystal
3:2 ratio of coformers	5	1:1 cocrystal, plus both coformers
3:2 ratio of coformers	198	3:2 cocrystal

Examination of the crystal structures of the 1:1 and 3:2 cocrystals show significant similarity: they both possess two terminal PPh_3O molecules, with sulfonamide molecules acting as bridges via hydrogen-bonding. This suggests that a third sulfonamide can "slot into" the structure of the 1:1 cocrystal in the grinding experiments to generate the 3:2 cocrystal.

To test this hypothesis, the following experiments were undertaken: (i) the 1:1 cocrystal was ground with TSA in a 1:1 ratio, (ii) the 1:1 cocrystal (1 equivalent) was ground with TSA (2 equivalents), and (iii) the 3:2 cocrystal was ground with Ph_3PO in a 1:1 ratio (Table 2 and Supporting Information). Experiments (i) and (ii) confirm that the 1:1 cocrystal can transform to the 3:2 cocrystal with excess sulfonamide present. Experiment (iii) shows that the 3:2 cocrystal does not transform to the 1:1 cocrystal when ground with an excess of Ph_3PO . PXRD analysis indicates no changes to either cocrystal over the period of eighteen months. Having examined the stability of the cocrystals in the solid state, we proceeded to undertake solution based stability studies.

Table 2. Effect of grinding the cocrystal with one coformer

<i>Material input</i>	<i>Grind time (min)</i>	<i>Material output</i>
1:1 cocrystal with TSA (1:1 ratio)	20	3:2 cocrystal plus TSA
1:1 cocrystal with TSA (2:1 ratio)	20	3:2 cocrystal
3:2 cocrystal with Ph ₃ PO (1:1 ratio)	20	3:2 cocrystal plus Ph ₃ PO

Solubility Measurements

The solubility values for TSA and Ph₃PO in each solvent at 20 °C are listed in Table 3. The order of solubility between TSA and Ph₃PO varies in the two solvents: TSA is more soluble than Ph₃PO in MeCN, but much less soluble than Ph₃PO in CH₂Cl₂. Ph₃PO is extremely soluble in CH₂Cl₂, exceeding the solubility of TSA by a factor of 35. It has been reported that the relative solubilities of the two cocrystal components in a solvent can be used to prepare a cocrystal in that solvent⁴, and a screening method has been developed around this concept.²³

Production of pure cocrystal forms using cooling crystallization was confirmed using PXRD (Figure 4). The solubility of the 1:1 cocrystal was successfully determined in MeCN. The concentration of TSA in a solution in equilibrium with the 1:1 cocrystal is lower than the concentration of TSA in a solution in equilibrium with pure TSA. The solubility of the 3:2 cocrystal could not be determined in MeCN. Equilibration of the 3:2 cocrystal in MeCN resulted in formation of the 1:1 cocrystal within 24 hours, a phenomenon known as incongruent dissolution.

Both cocrystals dissolved incongruently in CH₂Cl₂. Equilibration of the 3:2 cocrystal resulted in the formation of pure TSA, and equilibration of the 1:1 cocrystal resulted in the production of a mixture of the 3:2 cocrystal and TSA. Incongruent dissolution is an indication of an unsymmetrical ternary phase diagram, and usually occurs when there is a large difference in solubility between the 2 pure conforming phases in that solvent.⁴

Table 3. Measured Solubility Values for each Solid Form in MeCN and CH₂Cl₂ at 20 °C, Expressed in Terms of Mass Fraction (total mass basis, (MF)), and Molarity [M]

<i>Solid</i>	<i>Solvent</i>	<i>Solubility</i>				<i>Solid Phase at end of equilibration</i>
		MF _{TSA}	MF _{Ph₃PO}	MF _{solvent}	[M]	
TSA	MeCN	0.23	-	0.77	1.38	TSA
Ph ₃ PO		-	0.13	0.87	0.40	Ph ₃ PO
1:1 Cocrystal		0.04	0.06	0.90	0.19	1:1
3:2 Cocrystal			N/A			1:1
TSA	CH ₂ Cl ₂	0.01	-	0.99	0.11	TSA
Ph ₃ PO		-	0.44	0.56	3.80	Ph ₃ PO
1:1 Cocrystal			N/A			3:2 + TSA
3:2 Cocrystal			N/A			TSA

Experimentally determined invariant points in each solvent are expressed in terms of mass fraction in Table 4.

Table 4. Invariant points in MeCN and CH₂Cl₂ at 20 °C

<i>Solvent</i>	<i>Solid forms in equilibrium</i>	<i>Invariant Point (mass fraction, total mass basis)</i>		
		X _{TSA}	X _{Ph₃PO}	X _{Solvent}
MeCN	TSA + 3:2 (C ₁)	0.195	0.014	0.791
	3:2 + 1:1(C ₂)	0.087	0.041	0.871
	1:1 + Ph ₃ PO (C ₃)	0.018	0.150	0.832
CH ₂ Cl ₂	TSA + 3:2 (C ₁)	0.047	0.075	0.878
	3:2 + 1:1 (C ₂)	0.035	0.205	0.760
	1:1 + Ph ₃ PO (C ₃)	0.031	0.357	0.612

The ternary phase diagrams in MeCN and CH₂Cl₂ are presented in Figure 5 and Figure 6 respectively.




Figure 5: Ternary Phase Diagram for the TSA – Ph₃PO – MeCN system at 20 °C. Regions in the diagram are as follows: (1) solution phase; all other regions consist of a saturated solution in contact with (2) TSA only, (3) TSA + 3:2 cocrystal, (4) 3:2 cocrystal only, (5) 3:2 cocrystal + 1:1 cocrystal, (6) 1:1 cocrystal only, (7) 1:1 cocrystal + Ph₃PO, and, (8) Ph₃PO only. Values are in mass fractions.

TSA and Ph₃PO have a reasonably similar solubility in MeCN resulting in an approximately symmetrical ternary phase diagram. The 3:2 (region 4) and 1:1 (region 6) cocrystal are independently stable across a wide range of solution compositions. The 1:1 component stoichiometric line (solid line) intersects the solubility curve for the 1:1 cocrystal, indicating congruent dissolution for this cocrystal. Dissolution of the 1:1 cocrystal results in a solution with 1:1 molar stoichiometry, making it possible to experimentally measure the solubility of the 1:1 cocrystal in MeCN. In contrast, the 3:2 component

stoichiometric line (dashed line) does not intersect the solubility curve of the 3:2 cocrystal, explaining the observed incongruent dissolution of this form. This line instead intersects the solubility curve for the 1:1 cocrystal. Dissolution of the 3:2 cocrystal results in establishment of an equilibrium between a saturated solution and the 1:1 cocrystal.

In CH_2Cl_2 the significant difference in solubility between TSA and Ph_3PO results in an unsymmetrical diagram, with all regions skewed towards the Ph_3PO axis of the diagram. Both cocrystals dissolve incongruently, with dissolution of the 3:2 cocrystal initially resulting in solution of invariant composition in equilibrium with the 3:2 cocrystal and pure TSA (region 3), potentially continuing to a solution in equilibrium with pure TSA (region 2). Dissolution of the 1:1 cocrystal initially results in generation of a solution saturated with respect to the 1:1 and the 3:2 cocrystal (region 5), with continued dissolution resulting in solution composition moving to region 4, the region of stability for the 3:2 cocrystal. The 1:1 component stoichiometric line will eventually pass through the C_1 invariant point on this diagram, resulting in a saturated solution of invariant composition in equilibrium with the 3:2 cocrystal and pure TSA. In each case, the extent of dissolution will be controlled by the mass of the solvent present. The diagram is in good agreement with the phase conversions observed during efforts to measure cocrystal solubility (Table 3).




Figure 6: Ternary Phase Diagram for the TSA – Ph₃PO – CH₂Cl₂ system at 20 °C. Regions in the diagram are as follows: (1) solution phase; all other regions consist of a saturated solution in contact with (2) TSA only, (3) TSA + 3:2 cocrystal, (4) 3:2 cocrystal only, (5) 3:2 cocrystal + 1:1 cocrystal, (6) 1:1 cocrystal only, (7) 1:1 cocrystal + Ph₃PO, and, (8) Ph₃PO only. Values are in mass fraction, total mass basis.

Evaporation from a solution of 1:1 molar composition in either solvent may be visualized by following the solid line from the top apex of the diagram to the 1:1 cocrystal composition point. In MeCN, this line passes straight through region 6 making it possible to isolate the 1:1 cocrystal from this solution, regardless of the point at which evaporation is stopped. In CH₂Cl₂, evaporation of a solution of 1:1 molar composition could initially result in crystallization of pure TSA as the solid line skims the

solubility curve for TSA. Continued evaporation will move the solution composition into region 4, making it possible to isolate a pure 3:2 cocrystal product, but only if evaporation is stopped within this region. Further evaporation will result in concomitant crystallization of the 1:1 cocrystal as the solution composition moves into region 5. This demonstrates that the product of an evaporative crystallization can be dependent on the extent of solvent evaporation in a cocrystallization experiment, depending on the shape of the ternary phase diagram. A ternary phase diagram represents a system at thermodynamic equilibrium, and the above discussion is based on the assumption that thermodynamic equilibrium is maintained during the evaporation process. Crystallization is a dynamic process in which kinetic and thermodynamic factors compete to determine the solid product form, with kinetic factors most likely to promote the formation of a metastable product, but this is not specifically addressed in this work.

The same seven solid form regions (regions 2-8) were observed in each solvent, but the choice of solvent did affect the positioning of each solid form region within the ternary phase diagram. The shape of a ternary phase diagram is dependent on the relative solubility of both coformers in that solvent. Selection of a solvent which has a particular affinity for either, or both, coformers is a means of controlling the shape of the ternary phase diagram, and the region of stability for the desired crystal form.

Conclusions

A novel 1:1 cocrystal of *p*-toluenesulfonamide and triphenylphosphine oxide has been obtained by crystallizing the two coformers from acetonitrile, and single crystal analysis successfully applied to identify the new crystal structure. The 1:1 cocrystal has some structural similarity to the known 3:2 cocrystal, with the latter related by a simple incorporation of an extra sulfonamide molecule between two bridging phosphine oxide molecules.

Construction of the ternary phase diagram for *p*-toluenesulfonamide and triphenylphosphine oxide in MeCN and CH₂Cl₂ clearly identified regions of stability for the 1:1 and 3:2 cocrystal in these solvents, allowing for rationalization of the experimental isolation of the 1:1 cocrystal from a solution of 1:1

molar stoichiometry in MeCN, and the 3:2 cocrystal from a solution of 1:1 molar stoichiometry in CH₂Cl₂. This result demonstrates that solution stoichiometry during cocrystal preparation or screening does not necessarily reflect the stoichiometry of the resulting cocrystal. The solubility of both cocrystal coformers must be taken into consideration when performing a cocrystal search to ensure that cocrystals are discovered and that those of different stoichiometry are not missed.

Congruent and incongruent cocrystal dissolution was observed in MeCN for the 1:1 and the 3:2 cocrystal respectively, with both cocrystals dissolving incongruently in CH₂Cl₂. Incongruent dissolution prevents the measurement of pure cocrystal solubility with traditional methods, as it becomes impossible to equilibrate the pure cocrystal in the pure solvent to generate the required saturated solution. Incongruent dissolution is likely when there is a significant difference between the solubility of the pure coformers in the solvent.

Knowledge of the ternary phase diagram informs effective experimental design to control the desired cocrystal form. The choice of solvent in a cocrystal system has a major impact on the shape of the resulting ternary phase diagram.

Acknowledgment. This publication has emanated from research conducted with the financial support of Science Foundation Ireland under Grant Numbers 07/SRC/B1158 and 05/PICA/B802/EC07.


Supporting Information Available: X-ray crystallographic information in CIF format, DSC and PXRD data, and additional figures. The crystallographic data for the 1:1 cocrystal has been deposited with the Cambridge Crystallographic Data Centre, CCDC numbers 843627. These data can be obtained free of charge from The Cambridge Crystallographic Data Centre via www.ccdc.cam.ac.uk/data_request/cif. This material is available free of charge via the Internet at <http://pubs.acs.org>.

References

- (1) Schultesis, N.; Newman, A. *Cryst. Growth Des.* **2009**, *9*, 2950–2967.
- (2) Trask, A. V.; Jones, W. *Top. Curr. Chem.* **2005**, *254*, 41–70.
- (3) (a) Weyna, D. R.; Shattock, T.; Vishweshwar, P.; Zaworotko, M. J. *Cryst. Growth Des.* **2009**, *9*, 1106–1123. (b) Trask, A. V.; Motherwell, W. D. S.; Jones, W. *Chem. Comm.* **2004**, 890–891.
- (4) Chiarella, R. A.; Davey, R. J.; Peterson, M. L. *Cryst. Growth Des.* **2007**, *7*, 1223–1226.
- (5) Ainouz, A.; Authelin, J.-R.; Billot, P.; Liebermann, H. *Int. J. Pharm.* **2009**, *374*, 82–89.
- (6) Chadwick, K.; Davey, R. J.; Sadiq, G.; Cross, W.; Pritchard, R. *CrystEngComm* **2009**, *11*, 412–414.
- (7) Jayasankar, A.; Reddy, L. S.; Bethune, S. J.; Rodriguez-Hornedo, N. *Cryst. Growth Des.* **2009**, *9*, 889–897.
- (8) Yu, Z. Q.; Chow, P. S.; Tan, R. B. H. *Cryst. Growth Des.* **2010**, *10*, 2382–2387.
- (9) Nehm, S. J.; Rodríguez-Sprong, B.; Rodríguez-Hornedo, N. *Cryst. Growth Des.* **2006**, *6*, 592–600.
- (10) Chadwick, K.; Davey, R. J.; Dent, G.; Pritchard, R. G.; Hunter, C. A.; Musumeci, D. *Cryst. Growth Des.* **2009**, *9*, 1990–1999.
- (11) Arlin, J.-B.; Price, L. S.; Price, S. L.; Florence, A. J. *Chem. Comm.* **2011**, *47*, 7074–7076.
- (12) Schartmann, R. *Int. J. Pharm.* **2009**, *365*, 77–80.
- (13) Good, D. J.; Rodríguez-Hornedo, N. *Cryst. Growth Des.* **2010**, *10*, 1028–1032.
- (14) Good, D. J.; Rodríguez-Hornedo, N. *Cryst. Growth Des.* **2009**, *9*, (5), 2252–2264.

- (15) (a) Etter, M. C.; Baures, P. W. *J. Am. Chem. Soc.* **1988**, *110*, 639–40. (b) Aakeröy, C. B.; Salmon, D. J. *CrystEngComm* **2005**, *7*, 439–448.
- (16) Goud, N. R.; Babu, N. J.; Nangia, A. *Cryst. Growth Des.* **2011**, *11*, 1930–1939.
- (17) Ferguson, G.; Glidewell, C. *J. Chem. Soc. Perkin Trans.* **1988**, II, 2129–2132.
- (18) Ferguson, G.; Lough, A. J.; Glidewell, C. *J. Chem. Soc. Perkin Trans.* **1989**, II, 2065–2070.
- (19) *APEX2 v2009.3-0*; Bruker AXS: Madison, WI, **2009**.
- (20) Sheldrick, G. M. *Acta Crystallogr., Sect. A* **2008**, *64*, 112–122.
- (21) Macrae, C. F.; Bruno, I. J.; Chisholm, J. A.; Edgington, P. R.; McCabe, P.; Pidcock, E.; Rodríguez-Monge, L.; Taylor, R.; van de Streek, J.; Wood, P. A. *J. Appl. Crystallogr.* **2008**, *41*, 466–470.
- (22) Etter, M. C. *Acc. Chem. Res.* **1990**, *23*, 120–126.
- (23) Ter Horst, J. H.; Deji, M. A.; Cains, P. W. *Cryst. Growth Des.* **2009**, *9*, 3, 1531–1537.

For Table of Contents use only



A novel 1:1 cocrystal between *p*-toluenesulfonamide and triphenylphosphine oxide has been characterized. The relationship between this cocrystal and an existing 3:2 cocrystal in the solid state has been investigated. Ternary phase diagrams involving the two coformers have been constructed in two

different solvents, acetonitrile and dichloromethane, giving insight into the stability and solution crystallization of the 1:1 cocrystal and the 3:2 cocrystal.